



Product Code

ECT4305N-2400

- ◆ Glass Type
- ◆ Sizing Agent Code
- ◆ Roving Linear Density (Tex)

4305N demonstrates excellent dispersibility and superior compatibility with PP resins, offering outstanding processability that makes it ideally suited for LFRT (Long Fiber Reinforced Thermoplastics) and similar processes. This high-performance material finds wide application in automotive and electronics industries, among others.


Product Features		Technical Specifications			
● Consistent linear density ● Excellent processability ● Outstanding mechanical properties ● Superior convertibility ● White color	Fiber Diameter [μm]	Loss on ignition [%]	Moisture Content [%]	Tensile Strength [N/Tex]	
	ISO 1888	ISO 1887	ISO 3344	ISO 3341	
	17±1	0.35±0.10	≤0.10	≥0.30	

規格型号 Specification

Product Code	Glass Type	Fiber Diameter [μm]	Linear Density (Tex) [g/km]
ER4305N-2400	ECT	17	2400

包装与储存 Packaging & Storage

Packaging Method	Net Weight per Roll [kg]	Quantity per Pallet [个]	Pallet dimensions [mm]
Pallet Packaging	18-24	48	1140*1140*960
		64	1140*1140*1200
		36	950*1280*960
		48	950*1280*1200



Please store the glass fiber products in a dry and cool environment, with recommended temperature control between 10-30°C and humidity control between 50-75%. Stack pallets no more than 2 layers high.

